# TECHNICAL DATASHEET: **BEST ALTEZO**





# **TECHNICAL INFORMATION**



#### Layout dimensions

	layout dimensions (mm)			Number of pieces on the	consumption	quantity (m²)		weight (kg)			max. tonnage up to 24 t	
name	height	length	width	layer	pcs/m²	layer	pallet	layer	pallet	pallet included	pcs of pallets	m²
BEST ALTEZO	60	560	420	4	4.25	0.94	11.28	120	1440	1470	16	180.48

We are holders of the Gold Certificate for complete certification according to ISO 9001, ISO 14001, ISO 50001, ISO 45001. Our products are manufactured and inspected pursuant to European harmonized standards.

product height	production standard		tion from declared dimensions	bending strength	skid/slip resistance	ČSN 73 1326, weather resistance, method A	
	Stanuaru	width and length	height	Strength	resistance		
60 mm	ČSN EN 1339	±2 mm	±3 mm	≥ 5 MPa	≥ 40	≤ 1.0 kg/m² after 100 cycles	

#### **EXPLANATIONS OF PICTOGRAMS**





Surface





### **SURFACE FINISHES AND COLOURS**









NATURAL

COLORMIX ARABICA

COLORMIX BRILANT

COLORMIX SAND

surface	characteristics	colour
RELIEF	shaped surface with natural roughness, where the visible layer is formed by the height differences between the different levels of the stone	natural, colormix arabica, brilant, sand

## **GENERAL INFORMATION**

Two-layer vibrated paving with high strength, frost resistance, surface resistance to water and chemical de-icing agents. The paving has low abrasion and good adhesion properties. BEST concrete elements are permanently impregnated against contamination.

Minimum shipping quantity is 1 layer, stones cannot be shipped as single units. The goods are loaded on marked pallets BEST (30 kg) or BEST large (38 kg) according to the production capacity of individual plants.

When laying, it is important to follow the correct procedure according to the instructions for use (www.best.cz).

Caution: BEST ALTEZO paving is not intended for vehicle travel; we do not recommend compacting with a vibrating plate.







