

## TECHNICAL INFORMATION



Layout dimensions

name	layout dimensions (mm)			Number of pieces on the layer	consumption pcs/m <sup>2</sup>	quantity (m <sup>2</sup> )		weight (kg)			max. tonnage up to 24 t	
	height	length	width			layer	pallet	layer	pallet	pallet included	pcs of pallets	m <sup>2</sup>
BEST ATRIO 	60	560	280	6	6.38	0.94	11.28	120	1440	1470	16	180.48

We are holders of the Gold Certificate for complete certification according to ISO 9001, ISO 14001, ISO 50001, ISO 45001. Our products are manufactured and inspected pursuant to European harmonized standards.

product height	production standard	maximum deviation from declared production dimensions		bending strength	skid/slip resistance	ČSN 73 1326, weather resistance, method A
		width and length	height			
60 mm	ČSN EN 1339	±2 mm	±3 mm	≥ 5 MPa	≥ 40	≤ 1.0 kg/m <sup>2</sup> after 100 cycles

### EXPLANATIONS OF PICTOGRAMS



Paving designed for sidewalks, bicycle paths and non-motorized traffic.




Surface relief



Facet mini

## SURFACE FINISHES AND COLOURS




COLORMIX ETNA



COLORMIX ARABICA



COLORMIX BRILANT



COLORMIX SAND

surface	characteristics	colour
RELIEF	shaped surface with natural roughness, where the visible layer is formed by the height differences between the different levels of the stone	colormix etna, arabica, brilant, sand

## GENERAL INFORMATION

Two-layer vibrated paving with high strength, frost resistance, surface resistance to water and chemical de-icing agents. The paving has low abrasion and good adhesion properties. BEST concrete elements are permanently impregnated against contamination.

Minimum shipping quantity is 1 layer; stones cannot be shipped as single units. The goods are loaded on marked pallets BEST (30 kg) or BEST large (38 kg) according to the production capacity of individual plants.

When laying, it is important to follow the correct procedure according to the instructions for use ([www.best.cz](http://www.best.cz)).

**Caution:** BEST ATRIO paving is not intended for vehicle travel; we do not recommend compacting with a vibrating plate.



703/2020

