

TECHNICAL INFORMATION



Layout dimensions

name		layout dimensions (mm)			number of pieces on one layer	quantity (m ²)		weight (kg)			max. tonnage up to 24 tonnes		note
		height	length	width		layer	pallet	layer	pallet	pallet included	number of pallets	m ²	
BEST URIKO I		60	160	160	35	0.90	10.80	115	1380	1410	17	183.60	1 pallet = 12 layers
BEST URIKO II		60	240	160	25	0.96	11.52	123	1476	1506	15	172.80	1 pallet = 12 layers
BEST URIKO III		60	160	80	70	0.90	10.80	115	1380	1410	17	183.60	1 pallet = 12 layers
BEST URIKO I		80	160	160	35	0.90	9.00	153	1530	1560	15	135.00	1 pallet = 10 layers
BEST URIKO II		80	240	160	25	0.96	9.60	163	1630	1660	14	134.40	1 pallet = 10 layers
BEST URIKO III		80	160	80	70	0.90	9.00	153	1530	1560	15	135.00	1 pallet = 10 layers

We are holders of the Gold Certificate for complete certification according to ISO 9001, ISO 14001, ISO 50001, ISO 45001. Our products are manufactured and inspected pursuant to European harmonized standards.

product height	production standard	maximum deviation from declared production dimensions		transverse tensile strength	skid/slip resistance	ČSN 73 1326, weather resistance, method A
		width and length	height			
60 mm	ČSN EN 1338	±2 mm	±3 mm	≥ 3.6 MPa	satisfactory	≤ 1.0 kg/m ² after 100 cycles
80 mm	ČSN EN 1338	±2 mm	±3 mm	≥ 3.6 MPa	satisfactory	≤ 1.0 kg/m ² after 100 cycles

EXPLANATIONS OF PICTOGRAMS



Paving designed for sidewalks, bicycle paths and non-motorized traffic.



Paving intended for sidewalks, bicycle paths, parking spaces and movement of motor vehicles up to 3.5 t with occasional movement over 3.5 t (garbage trucks, supply).




Surface relief



No facet


SURFACE FINISHES AND COLOURS



NATURAL



COLORMIX AUTUMN



COLORMIX SAHARA

surface	characteristics	colour
RELIEF	shaped surface with natural roughness, where the visible layer is formed by the height differences between the different levels of the stone	natural, colormix autumn, colormix sahara

GENERAL INFORMATION

Two-layer vibrated paving with high strength, frost resistance, surface resistance to water and chemical de-icing agents. The paving has low abrasion and good adhesion properties. BEST concrete elements are permanently impregnated against contamination.

Minimum shipping quantity is 1 layer, stones cannot be shipped as single units. The goods are loaded on marked pallets BEST (30 kg) or BEST large (38 kg) according to the production capacity of individual plants.

When laying, it is important to follow the correct procedure according to the instructions for use (www.best.cz).

Caution: BEST URIKO paving with a height of 60 mm is recommended to be compacted with a vibrating plate with a plastic pad weighing no more than 100-130 kg with a set centrifugal force of 18-20 kN; paving with a height of 80 mm must be compacted with a vibrating plate with a plastic pad weighing no more than 170-200 kg with a set centrifugal force of 20-30 kN.

